

CALCINED BAUXITE

86

CHEMICALS				
Range				
Al₂O₃ (%)	Na ₂ O(%)	Fe ₂ O ₃ (%)	SiO ₂ (%)	TiO ₂ (%)
86%min.	0.4max.	2max.	8max.	4max.

PHYSICAL				
Range				
Particle Size	0-1mm			
	1-3mm			
	3-5mm		90min.	
	200mesh			
Bulk Density				3.2g/cm ³



Packing:

- 1,000KG woven bag

Application:

- Steel plant castable.
- Refractory.